



Tekniske egenskab	Resultat	Testmetode
Temperaturområde*	Slanger -40°C - +150°C Plader & tape -40°C - +130°C	EN 14707 EN 14706
Varmeledningsevne λ Ved en middeltemperatur = +40°C	$\leq 0,038$ W/m·K	EN 12667/ EN ISO 8497
Vanddampdiffusionmodstand	≥ 2500	EN 13469/ EN 12086
Brandklasse	Klasse E	EN 13501-1
Ozonbestandig	Meget god	ISO 7326
UV Bestandig	Meget god	UNI ISO 4892-2
Antimicrobial	Opfylder kravene	AATCC test metode 30-2004
Risiko for korrosion	Opfylder kravene	EN 13468

* Ved temperaturer under -40°C tag venligst kontakt til vores tekniske afdeling.



Vi tager forbehold for fejl

Isoglobal, Rellerriege 26, DE-33161 Hövelhof
www.isoglobal.dk